

Cargill Altor® 200 polyaspartic ester

Product Description

Altor® 200 polyaspartic ester is an ultra-fast reacting, low-color, solvent-free, amine-functional co-reactant for polyisocyanates. Altor® 200 polyaspartic ester was developed for high-solids, two-component polyurethane and urea coatings. The Altor® products can be applied direct to metal as one-coat solutions in environments with low to moderate protection needs. For extreme environments, the polyaspartic coating can act as the intermediate and topcoat in one layer, increasing productivity and reducing operation costs.

Altor® 201 or Altor® 202 products can be blended with Altor® 200 polyaspartic ester to obtain customized work and dry time characteristics when formulating high-solids polyurea topcoats. For polyaspartic products, humidity and substrate moisture control is crucial as water accelerates curing.

Applications

- Concrete coatings
- Infrastructure steel surfaces
- Railcar exterior coatings
- Cleanroom coatings
- Institutional coatings
- Flexible roof coatings
- Windmill coatings – towers & blades

Advantages

- Low color
- Low VOC
- UV and chemical resistant
- Compatible with many polyisocyanates and prepolymers
- Ultra-fast curing and return-to-service

Typical Properties

	TYPICAL VALUE	UNIT OF MEASURE
Color	70	APHA
Moisture	0.03	%
Viscosity @ 25°C	75	cP
Density @ 25°C	8.82	lb/gal
Amine Value	243	mg KOH/g sample
Amine Equivalent Weight	Approx. 234	AEW
Gel Time	< 2	min

Note: Data is based on lab testing performed with HDI hexamethylene diisocyanate (NCO content 22.5-23.9%).

Compatibility

Altor® 200 polyaspartic ester is compatible with most polyisocyanates, however, compatibility testing prior to large-scale application is recommended to ensure safe use.

Packaging, Storage, and Handling

Product is available in drums and totes. Keep away from extreme heat, cold, and moisture. Please refer to the product's safety data sheet for shipping, safety, and handling.

Note: It is recommended that opened drums use a desiccant tube in the bleed bung and are covered with a nitrogen blanket if the drum will be stored as a partial for later use.

Shelf Life

The recommended shelf life is 12 months in unopened containers maintained at a proper storage temperature of 25°C.

Environmental and Safety

Please refer to the product's safety data sheet.

If you have further questions do not hesitate to **reach out to your local representative.**

This document is provided for your information and convenience only. All information, statements, recommendations and suggestions are believed to be true and accurate but are made without guarantee, express or implied. WE DISCLAIM, TO THE FULLEST EXTENT PERMITTED BY LAW, ALL WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE and FREEDOM FROM INFRINGEMENT and disclaim all liability in connection with the storage, handling or use of our products or information, statements, recommendations and suggestions made by Cargill. All such risks are assumed by you/user. The labeling, substantiation and decision making relating to the regulatory approval status of, the labeling on and claims for your products is your responsibility. We recommend you consult regulatory and legal advisors familiar with applicable laws, rules and regulations prior to making regulatory, labeling or claims decisions for your products. The information, statements, recommendations and suggestions contained herein are subject to change without notice. Tests conducted by Cargill labs unless otherwise noted.

©2022 Cargill, Incorporated. All rights reserved.